

150~380M





High Efficiency Low LID Mono PERC with MBB & Half-cut Technology



Complete System and Product Certifications

IEC 61215, IEC 61730, UL 61730

ISO 9001:2008: ISO Quality Management System

ISO 14001: 2004: ISO Environment Management System OHSAS 18001: 2007 Occupational Health and Safety







* Specifications subject to technical changes and tests. LONGi Solar reserves the right of interpretation. Positive power tolerance (0 ~ +5W) guaranteed

High module conversion efficiency (up to 20.9%)

Slower power degradation enabled by Low LID Mono PERC technology: first year <2%, 0.55% year 2-25

Solid PID resistance ensured by solar cell process optimization and careful module BOM selection

Reduced resistive loss with lower operating current

Higher energy yield with lower operating temperature

 $\textbf{Reduced hot spot risk} \ \text{with optimized electrical design and lower operating current}$



LONGi Green Energy Technology Co., Ltd.

Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.

LR4-60HPH **350~380M**

Design (mm)

35 1038 4.5 103

Mechanical Parameters

Cell Orientation: 120 (6×20)

Junction Box: IP68, three diodes

Output Cable: 4mm², 1200mm in length

Connector: Staubli EVO2

Glass: Single glass

3.2mm coated tempered glass

Frame: Anodized aluminum alloy frame

Weight: 19.5kg

Dimension: 1755×1038×35mm Packaging: 30pcs per pallet

100---- 20/0

780pcs per 40'HC

180pcs per 20'GP

Operating Parameters

Operational Temperature: -40 $^{\circ}$ C ~+85 $^{\circ}$ C Power Output Tolerance: 0 ~+5 $^{\circ}$ W Voc and Isc Tolerance: $\pm 3\%$

Maximum System Voltage: DC1500V (IEC/UL)

Maximum Series Fuse Rating: 20A

Nominal Operating Cell Temperature: 45±2 °C

Safety Protection Class: Class II

Fire Rating: Class C according to UL790


Model Number	LR4-60H	PH-350M	LR4-60H	PH-355M	LR4-60H	PH-360M	LR4-60HI	PH-365M	LR4-60H	PH-370M	LR4-60H	PH-375M	LR4-60H	PH-380N
Testing Condition	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT	STC	NOCT
Maximum Power (Pmax/W)	350	261.4	355	265.1	360	268.8	365	272.6	370	276.3	375	280.0	380	283.8
Open Circuit Voltage (Voc/V)	40.1	37.6	40.3	37.8	40.5	38.0	40.7	38.2	40.9	38.3	41.1	38.5	41.3	38.7
Short Circuit Current (Isc/A)	11.15	9.02	11.25	9.10	11.35	9.17	11.43	9.25	11.52	9.32	11.60	9.38	11.69	9.45
Voltage at Maximum Power (Vmp/V)	33.6	31.3	33.8	31.5	34.0	31.7	34.2	31.8	34.4	32.0	34.6	32.2	34.8	32.4
Current at Maximum Power (Imp/A)	10.42	8.35	10.51	8.43	10.59	8.49	10.68	8.56	10.76	8.63	10.84	8.69	10.92	8.76
Module Efficiency(%)	19	.2	19	.5	19	.8	20	0.0	2	0.3	20).6	20).9

NOCT (Nominal Operating Cell Temperature): Irradiance 800W/m², Ambient Temperature 20 C, Spectra at AM1.5, Wind at 1m/S


Temperature Ratings (STC)		Mechanical Loading						
Temperature Coefficient of Isc	+0.048%/°C	Front Side Maximum Static Loading	5400Pa					
Temperature Coefficient of Voc	-0.270%/ °C	Rear Side Maximum Static Loading	2400Pa					
Temperature Coefficient of Pmax	-0.350%/ °C	Hailstone Test	25mm Hailstone at the speed of 23m/s					

I-V Curve


Current-Voltage Curve (LR4-60HPH-365M)



Power-Voltage Curve (LR4-60HPH-365M)



Current-Voltage Curve (LR4-60HPH-365M)







McNae Electrical Solutions Ltd

MAIL | PO Box 9086, Palmerston North 4441

OFFICE | 451 Kairanga Bunnythorpe Rd, RD8, Palmerston North 4478

T | 06 3570405 **W** | mcnae.co.nz

E | info@mcnae.co.nz

Note: Due to continuous technical innovation, R&D and improvement, technical data above mentioned may be of modification accordingly. LONGi have the sole right to make such modification at anytime without further notice; Demanding party shall request for the latest datasheet for such as contract need, and make it a consisting and binding part of lawful documentation duly signed by both parties.